



# Nitoflor SL2000

## Flow applied, 2mm thick epoxy resin based floor topping

### Uses

Nitoflor SL2000 is designed for use in wide range of industrial environments where a lasting solution to floor maintenance problems is required. It provides a dense, impervious, coloured and chemically resistant floor surface which is hygienic and easy to clean. Typical applications include:

- Clean rooms
- Laboratories
- Kitchens
- Plant rooms
- Light industrial plants

### Advantages

- **Fast application** - minimises downtime
- **Chemically resistant** - good resistance to a wide range of chemicals
- **Durable** - good abrasion resistance
- **Hygienic** - provide a dense, impervious, seamless floor surface which is easily cleaned
- **Attractive** - available in a wide range of colours to enhance the working environment

### Description

Nitoflor SL2000 consists of graded aggregates bound in a pigmented epoxy resin binder. It is supplied as a fourcomponent system, pre-weighed for on-site mixing.

When laid, it provides a smooth, light-reflective surface. It is available in a range of standard colours.

### Specification

#### Flow-applied epoxy floor topping

The designated floor areas shall be surfaced with Nitoflor SL2000, a 2 mm thick flow-applied epoxy resin floor topping. The topping shall achieve a minimum compressive strength of 40 N/mm<sup>2</sup> and a flexural strength of 25 N/mm<sup>2</sup> at 7 days when tested to BS6319. At 20°C, it shall be capable of accepting foot traffic at 24 hours and vehicular traffic at 48 hours.

#### Properties

The values given below are average figures achieved in laboratory tests. Actual values obtained on site may show minor variations from those quoted.

Pot Life	@ 25°C	@35°C
----------	--------	-------

Nitoflor SL2000	: 1 hour	20 min
-----------------	----------	--------

Nitoprime 25	: 3-4 hours	1-1.5 hours
--------------	-------------	-------------

Nitocote Primer Sealer	: 2.0 hours	1 hour
------------------------	-------------	--------

Cure time-		
Foot traffic	: 24 hours	16 hours
Vehicular traffic	: 48 hours	36 hours
Chemical resistance	: 7 days	4 days

#### Physical properties

Mixed density	: 1.72 g/cc
---------------	-------------

Compressive strength @7 days (BS 6319)	: 50 N/mm <sup>2</sup>	50 N/mm <sup>2</sup>
--	------------------------	----------------------

Flexural strength @7 days (BS 6319)	: 34 N/mm <sup>2</sup>	34 N/mm <sup>2</sup>
-------------------------------------	------------------------	----------------------

Tensile strength @7 days (BS 6319)	: 12 N/mm <sup>2</sup>	12 N/mm <sup>2</sup>
------------------------------------	------------------------	----------------------

Abrasion resistance :	0.1mg/ cycle-loss of weight (ASTM D 4060) (with CS 17 wheel of 1000g weight)	
-----------------------	--	--

Shore D Hardness as per (ASTM D 2240)	: 80
---------------------------------------	------

Adhesion Strength @ 7 days (ASTM D412)	: > 1N/mm <sup>2</sup>
--	------------------------

Slip resistance	: 91.3 & 135.6 (As per TRRL skid test in accordance with BS 6677 : Part 1:1986)
-----------------	---

#### Chemical Properties

Nitoflor SL2000 has excellent resistance at ambient temperatures to a wide range of industrial chemicals. Specific data is available on request.

Note that it is especially important that spillage is cleaned up quickly since much higher concentrations of chemicals may occur on evaporation.

#### Design criteria

Nitoflor SL2000 is designed for application at a nominal thickness of 2mm.

# Nitoflor SL2000

---

Substrates should be dry and not suffer, or be likely to suffer, from rising damp. If necessary, suitable damp-proof membranes should be installed during construction to prevent this. Substrates should not have a relative humidity greater than 75% at the time of installation.

## Instructions for use

Nitoflor SL2000 should be applied by specialist contractors who must follow the procedures laid down in the Product Method Statement. Fosroc works with a network of such applicators who have been trained in the correct installation procedures. The following steps are involved in the application which would normally take place over a 2 to 3 day period depending on the areas involved.

## Surface Preparation

It is essential that Nitoflor SL2000 is applied to sound, clean and dry surfaces in order that maximum bond strength is achieved between the substrate and the flooring system. All dust and debris should be removed prior to application of the product or its primer.

## New concrete floors

New concrete, or cementitious substrates, should be at least 28 days old and have a moisture content not exceeding 5%. Laitance deposits on new concrete are best removed by light grit blasting, mechanical scabbling or grinding.

## Old concrete floors

Existing concrete floors which require refurbishment must be prepared to ensure a strong adhesive bond between the flooring system and the existing floor. Mechanical cleaning methods are strongly recommended particularly where heavy contamination by oil and grease has occurred or existing coatings are present. To ensure adhesion, all contamination should be removed.

Alternatively, blasting techniques can be used to provide the required substrate

## Steel surfaces

Steel surfaces should be degreased and grit blasted to SA2½ immediately prior to application. The prepared surface should then be treated with one coat of Nitoprime 28.

## Priming

All surfaces to be treated with Nitoflor SL2000 should be primed with Nitoprime 25, a solvent based epoxy resin primer designed for maximum absorption and adhesion to concrete substrates.

Add the entire contents of the hardener tin to the base tin and mix the two primer components thoroughly for at least 2 minutes - under no circumstances should part mixing be considered.

Once mixed, the primer should be applied immediately to the prepared substrate using stiff brushes and/or rollers. The primer should be well 'scrubbed' into the substrate to ensure full coverage, but care should be taken to avoid over application or 'ponding'.

Allow the primer to dry (see table below) before proceeding to the next stage. Do not proceed whilst the primer is 'tacky' as this will lead to unsightly marks on the finished surface.

Porous substrates may require a second primer coat - when the first coat is directly absorbed into the substrate - but minimum overcoating times must still be observed (see table below).

The minimum overcoating times will vary slightly according to the porosity of the substrate. However, they should be in accordance with the following ambient application temperatures.

20°C	:	8-12 hours
30°C	:	6-8 hours
40°C	:	4-6 hours

## Mixing

Nitoflor SL flooring is supplied in four pre-weighed packs (base, hardener, aggregate and colour pack) which are ready for immediate on-site mixing. Part mixing of these components is not acceptable and will affect both performance and appearance of the finished floor.

Mixing should be carried out using either a forced action mixer; or a heavy duty, slow-speed drill fitted with mixing paddle. All such equipment should be of a type and capacity approved by Fosroc. The components should be mixed in a suitably sized mixing vessel.

The colour pack should be added to the base container and mixed for 15-30 seconds, until homogeneous. Then add the hardener and mix for further 30 seconds, until an even colour and texture is obtained.

Thereafter, the contents of the graded aggregate pack should be slowly added and mixing carried out for a further 3 minutes until a completely homogenous material is obtained.



# Nitoflor SL2000

## Application

The applicator should ensure that there are sufficient supplies of plant, labour and materials to make the mixing and subsequent application process a continuous one for any given, independent floor area.

Once mixed, the material must be used within its specified pot life - see "Properties" section.

The material should be poured onto the prepared and primed substrate as soon as mixing is complete. It should be spread to the required thickness using a serrated trowel; with care taken not to overwork the resin, spreading evenly and slowly. Immediately after laying, the material should be rolled, using a spiked nylon roller, to remove slight trowel marks, and to assist air release. The rolling should be carried out using a 'back and forth' technique along the same path. An overlap of 50% with adjacent paths is recommended.

Further light rolling may be required to remove surface imperfections, or for subsequent release of trapped air, but should be prior to the setting of the product.

## Floor Joints

All existing expansion or movement joints should be followed through the new floor surface.

Joint sealant & joint geometry should be compatible with the floor type used, intended exposure conditions and likely movement characteristics of the substrate - consult the local Fosroc office for more details.

## Cleaning

Nitoprime 25, and Nitoflor SL2000 should be removed from tools and equipment with Fosroc Nitoflor Sol immediately after use. Hardened material can only be removed mechanically.

## Maintenance

The service life of a floor can be considerably extended by good housekeeping. Regular cleaning may be carried out using a rotary scrubbing machine with a water miscible cleaning agent at temperatures up to 50°C.

## Technical support

Fosroc offers a comprehensive range of high performance, high quality, flooring, jointing and repair products for both new and existing floor surfaces. In addition, the company offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.



## Limitations

- Nitoflor SL2000 should not be applied on to surfaces known to, or likely to suffer from, rising dampness, potential osmosis problems or have a relative humidity greater than 75% as measured in accordance with BS 8203 Appendix A, or by protimeter.
- In areas where significant thermal shock is likely to occur, please consult the local Fosroc office.
- Nitoflor SL2000 should not be applied to asphalt, weak or friable concrete, unmodified sand/cement screeds, PVC tiles or sheet or substrates known to move substantially e.g. steel walkways. For information on other substrates, consult the local Fosroc office.
- Nitoflor SL2000 should not be installed at temperatures below 10°C or above 45°C. If in doubt, or for application outside these temperature limits, please consult your nearest Fosroc office.
- In common with all epoxy materials some light shade changes may be experienced over the long term when placed in adverse exposure conditions. Any such change in shade is not regarded as being detrimental to performance.

## Estimating

### Supply

<b>Nitoflor SL2000</b>	:	15 litre pack (incl. colour pack)
------------------------	---	--------------------------------------

<b>Nitoprime 25</b>	:	1 and 4 litre packs
---------------------	---	---------------------

<b>Nitoflor Sol</b>	:	5 and 20 litre tins
---------------------	---	---------------------

### Coverage

<b>Nitoflor SL2000</b>	:	7.5 m <sup>2</sup> /pack @ 2 mm thickness
------------------------	---	--

<b>Nitoprime 25</b>	:	5.5 - 6.5 m <sup>2</sup> / litre
---------------------	---	----------------------------------

Note : The coverage figures given are theoretical. Due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced. Typically, an additional 10% should be allowed for surface irregularities and wastage although this will vary with site conditions.

## Storage

### Shelf life

Nitoflor SL2000 has a shelf life of 12 months if kept in warehouse conditions at 30°C in the original, unopened pack.

### Storage conditions

Store in dry conditions between 5°C and 30°C, away from sources of heat and naked flames, in the original, unopened packs. If stored at high temperatures the shelf life will be reduced.

# Nitoflor SL2000

## Precautions

### Health and safety

Nitoflor SL2000, Nitoprime 25, Nitoprime 28 and Nitoflor Sol should not come in contact with the skin and eyes, or be swallowed.

Ensure adequate ventilation and avoid inhalation of vapours. Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye protection.

In case of contact with skin, rinse with plenty of clean water, then cleans with soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

### Fire

Nitoprime 25 and Nitoflor Sol are flammable. Keep away from sources of ignition. No smoking. In the event of fire extinguish with CO<sub>2</sub> or foam. Do not use a water jet.

Nitoflor SL2000 is non-flammable.

### Flash points

Nitoprime 25 : 39°C  
Nitoflor Sol : 33°C



## Fosroc Chemicals (India) Pvt. Ltd.

### Head Office

"Sapthagiri Palace", No.38,  
II & III Floor, 12th Cross,  
CBI Road, Ganganagar North,  
Bangalore 560 032

### Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

### telephone

++91 80-23551500

### fax

++91 80-23551510

### e-mail

enquiryindia@fosroc.com

### Regional Offices

#### Bangalore

"Sapthagiri Palace", No. 38  
II & III Floor, 12th Cross,  
CBI Road, Ganganagar North,  
Bangalore 560 032.  
Ph:080-23551500  
Fax : 080-23551510

#### Mumbai

1401/1402, 14floor,  
A-Wing 'The Great Eastern Summit'  
Sector-15, CBD, Belapur  
Navi Mumbai 400 614  
Ph: 022 -43406800-04

#### Delhi

D-166 Sector 10  
Noida,  
UP 201 301  
Ph:0120-4270620  
Fax: 033-2499-0280

#### Kolkata

304, Jodhpur Park  
Kolkata 700 068  
Ph:033-65343188

## Disposal

Spillages of component products should be absorbed on to earth, sand or other inert material and transferred to a suitable vessel. Disposal of such spillages or empty packaging should be in accordance with local waste disposal regulations.

For further information, refer to the Product Material Safety Data Sheet.

## Additional information

Fosroc manufactures a wide range of complementary products which include :

- waterproofing membranes & waterstops
- joint sealants & filler boards
- cementitious & epoxy grouts
- specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following :

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office - as below.

