



Reebol Emulsion Xtra

Concentrated and emulsified chemical mould release agent

Uses

For easy and stain free release of concrete moulds and formwork of all types. Particularly where wooden formwork is used and de-moulding or stripping times exceed 24 hours.

Advantages

- **Non-staining** : No cleaning of unsightly oil stains if plastering is not required.
- **High quality** : Produces really fair faced finish concrete.
- **Versatile** : Can be used on all types of moulds.
- **Minimises cleaning** : Makes cleaning of form faces between pours very easy.
- **Concentrate form** : Reduces storage and transport costs.
- **Water based** : Only requires water for dilution.
- Aids corrosion inhibition

Description

Reebol Emulsion Xtra is supplied as a pale amber liquid which turns white when diluted with water to produce a chemical release agent, combining the outstanding release properties of such materials with the economy of a conventional oil. It reacts with the alkali in the concrete to form a thin water repellent skin on the surface of the mould which enables easy stripping from the hardened concrete.

Technical Support

Fosroc offers a comprehensive range of high performance, high quality concrete repair and construction products. In addition, Fosroc offers technical support service to specifiers, end-users and contractors, as well as on-site technical assistance in locations all over the country.

Properties

Dilution rate - 1 part Reebol Emulsion Xtra: 6parts clear water (by volume)

Formwork surfaces - May be used on wooden or metal surfaces. Particularly effective on resinous coated surfaces including Reebol Formcote coated wooden surfaces.

Non-staining - Can be used safely with white cement.

Specific Gravity - Typically 0.960 at 25°C

Application instructions

Mixing

First dilute Reebol Emulsion Xtra concentrate in the proportion of 1:6 with water, using a clean container and stirring thoroughly until evenly mixed. If the solution is not used the same day, it should be stirred again before use and may require very good stirring after 5 days.

New Moulds : No preparation is normally necessary Metal moulds showing signs of rust, must be wire brushed or treated with emery cloth and burnished clean before coating.

New timber : Plywood will give superior results and much extended re-use if first coated with Reebol Formcote.

Used moulds : Must be thoroughly clean and free from old concrete, dirt, cement laitence, old mould oil and other contaminations. Use a strong detergent for removal of oil and grease; Reebaklens for cement and concrete deposits.

Application : Apply the Reebol Emulsion Xtra 1:6 water dilution to the face of the formwork by spray, brush or cloth. Only one coat should be applied (as thinly as possible except on very absorbent new timber where two coats may be necessary for the first application only) and allow to dry.

If the formwork is not used for several days, a further coat may be applied.

Only a very thin film of Reebol Emulsion Xtra should be applied. Excess could lead to surface dusting of the concrete.

The best results are obtained by applying with a fine mist sprayer. Where a cloth is used, it should first be soaked in the release agent and then squeezed out well before applying. This ensures the thinnest possible film. Reebol Emulsion Extra is not generally recommended where demoulding is required within 24 hours, although excellent results may be obtained with shorter times.

Drying time : It is essential that the Reebol Emulsion Xtra is thoroughly dry before placing concrete. Otherwise, being an emulsion, its performance may be impaired. In condition of high humidity drying times will be much longer than in warm dry conditions.

Rainfall : It is necessary to protect freshly coated formwork from rain which may dilute the emulsion before it has dried. After drying the coating will withstand an occasional lighty shower but may be affected by heavy or continuous rain. In such cases, a further coat is advised once surfaces have dried out thoroughly.

Reebol Emulsion Xtra

De-moulding : De-moulding can be carried out in the normal way and no special precautions are necessary.

After de-moulding : Formwork surfaces must be thoroughly cleaned, but this is normally easy due to the excellent release action.

Before re-use : The cleaned formwork surfaces must be recoated with Reebol Emulsion Xtra each time, in accordance with normal practice.

Maintenance

Reebol Emulsion Xtra is an internationally used material and has an outstanding record of performance. On rare occasions the normally high level of performance is not achieved but in most cases, the problem is a simple one and easily identified by the following check list:

1. Are mould surfaces really clean before re-use?
2. Is a fresh coat of Reebol Emulsion Xtra applied before each re-use?
3. Has the Reebol Emulsion Xtra been diluted exactly 1:6 with water by volume?
4. Is the coverage rate the highest and the film thickness the lowest possible?
5. Is the coat really dry before placing the concrete? (remember a change in weather can alter drying times significantly).
6. Is the de-moulding time 24 hours or more?

If the answers to one or more of these questions is 'No', it usually explains the reason for the problem experienced which can be rectified accordingly.

Estimating

Packaging

Reebol Emulsion Xtra is supplied in 5,20 and 200 litre containers.

Coverage

1 litre of Reebol Emulsion Xtra when diluted with 6 litres of water will cover 80 to 180 m² depending upon the nature of the substrate.

The highest coverage rate must be aimed for - As a guide :
unsealed timber or plywood - 80 to 115 m² / 7 litres of solution.

Steel or sealed (Reebol Formcote coated) plywood - 120 to 180 m² / 7 litres of solution.

If coverage rates are appreciably less than these and satisfactory results are not being achieved, then coverages should be increased as close to the higher figure as possible.

Storage

Reebol Emulsion Xtra has a shelf life of 12 months provided the temperature is kept in the range of 5°C - 40°C. If this temperature is exceeded in any respect, advice should be sought from the supplier.

Diluted Reebol Emulsion Xtra will remain stable for at least 5 days but must be re-stirred before use.

Precautions

Health and safety instructions

Gloves should be worn when handling Reebol Emulsion Xtra. Splashes on skin should be removed with soap and water. Contact with eyes should be avoided and accidental contamination should be washed with plenty of water and medical treatment sought immediately. If swallowed, obtain immediate aid. Do not induce vomiting. Ensure good ventilation.

Reebol Emulsion Xtra

Fire

Flash point of Reebol Emulsion Xtra is approximately 61°C.

Additional information

Technical data and guidance can be provided on a wide range of admixtures, concreting aids, grouts, repairs and the Nitoflor range of industrial flooring systems which includes non metallic floor hardeners, epoxy floor coatings and self levelling floor toppings, epoxy heavy duty abrasion resistant screeds.

Separate datasheets are available on these products.

Reebol Emulsion Xtra



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

"Sapthagiri Palace", No.38,
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

++91 80-23551500

fax

++91 80-23551510

e-mail

enquiryindia@fosroc.com

Regional Offices

Bangalore

"Sapthagiri Palace", No. 38
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032.
Ph:080-23551500
Fax : 080-23551510

Mumbai

1401/1402, 14floor,
A-Wing 'The Great Eastern Summit'
Sector-15, CBD, Belapur
Navi Mumbai 400 614
Ph: 022 -43406800-04

Delhi

D-166 Sector 10
Noida,
UP 201 301
Ph:0120-4270620
Fax: 033-2499-0280

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph:033-65343188

www.fosroc.com

