



Nitocote® AP35

Latex acrylic polymer based cementitious coating

Uses

Provides passivating protection matrix to reinforcing steel

Advantages

- **Anticorrosive** - protects from future corrosion
- **High adhesion** - excellent bonding to all types of steel substrate
- **Cement based** - compatible with concrete
- **User friendly** - can be easily applied by brush

Description

Nitocote AP35, a single component latex acrylic polymer based emulsion is used for protecting steel reinforcement from corrosion.

It only needs to be mixed with cement at site to produce an easily brushable coating.

Technical support

Fosroc offers a technical support service to specifiers, end users and contractors, as well as on-site technical assistance in locations all over the country.

Properties

| | |
|---------------------------|---|
| Appearance | : Milky white liquid |
| Solid content | : Exceeds 35% |
| pH | : : 8 -9 |
| Specific gravity | : 1.04 @ 27°C |
| Application temperature | : Not less than 10°C |
| Adhesion to steel | : Excellent |
| Bond strength with cement | : Good |
| Toxicity | : Non-toxic |
| Mix proportions | : 1 part Nitocote AP35 acrylic polymer : 1.25 part cement |

Application instructions

Surface Preparation

Any corroded steel in the repair area and all loose scale and corrosion deposits should be fully exposed. Steel should be cleaned to a bright condition paying particular attention to the back of exposed steel bars. Grit-blasting is recommended for this process.

Where corrosion has occurred due to the presence of chlorides, the steel should be high-pressure washed with clean water immediately after grit-blasting to remove corrosion products from pits and imperfections within its surface.

Application

The application of Nitocote AP35 acrylic primer must take place as soon as possible to a dry steel surface after completion of the preparation work but always within 3 hours.

One full and unbroken coat of Nitocote AP35 acrylic primer shall be applied by suitable brush making sure the surfaces of the steel are properly coated. A small brush is generally suitable for this purpose. It shall be allowed to dry fully before continuing. If in doubt of having achieved an unbroken coating, a second application should be made as soon as the first coat is fully dry (generally between 45 minutes and one hour)

The application of concrete repair materials should proceed as soon as the Nitocote AP35 acrylic primer is fully dry (generally 45 mins. to 1 hour).

Minimum application temperature for Nitocote AP35 acrylic primer is 10°C.

Equipment cleaning

Immediately after use, all tools shall be washed with clean water.

Estimating

Packaging

Nitocote AP35 acrylic primer is supplied in 1, 5 and 20 litre plastic containers.

Coverage

Approximately 8 - 10 m²/ litre depending on substrate.

Nitocote® AP35

Storage

Shelf life

Nitocote AP35 acrylic primer has a shelf life of 6 months at 30°C. Nitocote AP35 acrylic primer should be protected from frost.

Precautions

Health & Safety instructions

Nitocote AP35 acrylic primer is non toxic. However it should never be ingested and if it comes into contact with eyes, it shall be washed immediately with plenty of water and medical advice shall be sought.

Nitocote AP35 acrylic primer is slightly alkaline. Skin contact should be avoided. Gloves and protective clothing should be worn during handling/application of the product.

Fire

Nitocote AP35 acrylic primer is non flammable.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

"Sapthagiri Palace", No.38,
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-23551500

fax

+91 80-23551510

e-mail

enquiryindia@fosroc.com

Regional Offices

Bangalore

"Sapthagiri Palace", No. 38
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032.
Ph:080-23551500
Fax : 080-23551510

Mumbai

1401/1402, 14floor,
A-Wing'The Great Eastern Summit'
Sector-15, CBD, Belapur
Navi Mumbai 400 614
Ph: 022 -43406800-04

Delhi

D-166 Sector 10
Noida,
UP 201 301
Ph:0120-4270620
Fax: 033-2499-0280

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph:033-65343188