

Nitotile Grout

(Formerly known as Nitotile GR)



constructive solutions

Pigmented cementitious tiles joint filler

Uses

As a grout for dry tile joints in:

- Kitchens
- Bathrooms
- Shower stalls
- Swimming pools

Advantages

- Low cost service life - Mould resistant, tropical grade
- Easy to apply - Just add water for a thixotropic, non-slump grout
- Can be used in submerged conditions
- Available in a range of attractive colours

Description

Nitotile Grout is a blend of specially selected cements, fillers and synthetic organic polymers. When added to water it readily blends to produce a smooth creamy paste which when set is water and mould resistant. Nitotile Grout is used in conjunction with Nitotile* tile adhesives.

Properties

Specific gravity : 1.9 to 2.0 g/cc

Typical Properties of mixed material.

Working time at 20°C	: 90 minutes
Working time at 35°C	: 30 minutes
Compressive strength (ASTM C 109)	: 38 N/mm ² @ 28 days
Tensile strength (BS 6319: Pt 7)	: 3 N/mm ² @ 28 days

Instructions for use

Preparation

All tiles must be securely fixed in place and thoroughly cleaned before Nitotile Grout is applied. The gap between tiles should not exceed 4mm. Tile joint filling should only be done 24 hours after fixing the tiles.

Mixing

300 ml of water is required for each kg bag of Nitotile Grout. Add powder to water and mix until a uniform, lump-free, thick creamy paste is produced, allow to stand for ten minutes prior to use.

Application

Apply Nitotile Grout to the spaces between the tiles using a sponge or a small piece of soft cloth. Work the mixture into the joints and around the edges.

Remove surplus material from the face of the tiles with a dry cloth and run the tip of a gloved finger or suitable rounded tool along the grout to level it off and form a profile.

When the grout is dry, clean the tiles with a damp sponge to remove any excess material. It is advisable to remove uncured grout from textured tiles prior to setting, failure to do so may result in difficulty in removal.

Cleaning

Nitotile Grout should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed mechanically.

Limitations

Nitotile Grout should not be used when the temperature is below 5°C and falling. The product should not be exposed to moving water during application. If any doubts arise concerning temperature or substrate conditions, consult your local Fosroc office.

Estimating

Supply

Nitotile Grout : 1 kg pack

Coverage

Nitotile Grout : Approx. 49 running meter of 3mmx5mm joint / kg.

Storage

Shelf life

Nitotile Grout has a shelf life of 12 months if kept in a dry store in the original, unopened bags or packs.

Storage conditions

Store in dry conditions in the original, unopened bags or packs. If stored at high temperature and / or high humidity conditions the shelf life may be reduced.

Technical support

Fosroc offers a comprehensive range of high performance, high quality repair, maintenance and construction products.

Nitotile Grout

(Formerly known as Nitotile GR)

In addition, Fosroc offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance in locations all over the world.

Precautions

Health and safety

Nitotile Grout is cement based. Care should be taken to avoid inhalation of dust and contact with eyes. All cement based products, when mixed or damp release alkalis which can be harmful to the skin.

Additional Information

Nitotile Grout is part of a range of Fosroc tile adhesives and tile grouts.

Fosroc manufactures a wide range of complementary products which include:

- Waterproofing membranes & waterstops
- Joint sealants & filler boards
- Cementitious & epoxy grouts
- Specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following:

- Hand-placed repair mortars
- Spray grade repair mortars
- Fluid micro-concretes
- Chemically resistant epoxy mortars
- Anti-carbonation/anti-chloride protective coatings
- Chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

"Sapthagiri Palace", No.38,
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

++91 80-23551500

fax

++91 80-23551510

e-mail

enquiryindia@fosroc.com

Regional Offices

Bangalore

"Sapthagiri Palace", No. 38
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032.
Ph:080-23551500
Fax : 080-23551510

Mumbai

1401/1402, 14floor,
A-Wing'The Great Eastern Summit'
Sector-15, CBD, Belapur
Navi Mumbai 400 614
Ph: 022 -43406800-04

Delhi

D-166 Sector 10
Noida,
UP 201 301
Ph:0120-4270620
Fax: 033-2499-0280

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph:033-65343188

