

Proofex GP

(Formerly Proofex GPX)



constructive solutions

Cold applied bituminous waterproofing membrane

Uses

To provide a continuously bonded waterproof membrane for building and civil engineering structures.

Advantages

- 1.5mm± 0.05 thick (Nominal)
- Cold applied
- Fast application
- Uniform thickness of polymer bitumen membrane
- Good adhesion to primed concrete substrates.
- Produces a continuous waterproof membrane system

Description

Proofex GP is a cold applied self-adhesive sheet membrane comprising of a polymer modified bitumen layer internally reinforced with polyester, bonded on to an outer surface of cross laminated polyethylene film.

The polymer bitumen adhesive layer is protected on the underside by a silicone release paper which is removed just prior to the application of Proofex GP to the tack coat primed substrate.

The applied membrane is then immediately protected from UV light and from mechanical damage during subsequent back filling by the application of Protection Board, or a sand/cement screed.

Specification

The waterproofing membrane shall be a 1.6mm thick self adhesive sheet membrane comprising of a polymer modified bitumen layer internally reinforced with polyester, bonded on to an outer surface of polyethylene film. The polymer modified bitumen shall have an elongation in excess of 2000% when tested in accordance with ASTM D412.

Technical Support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Properties

Tensile strength : Long 39 N/mm²
(ASTM D638:1991) Trans 46 N/mm²

Elongation of membrane : Long 250%
(ASTM D638:1991) Trans 200%

Elongation of compound : >2000%
(ASTM D412)

Tear resistance : Long 280 N/mm

(ASTM D 146)

Adhesion to concrete

(ASTM D1000) : 2.2 N/mm²

Adhesion to self

(ASTM D1000) : 3.5 N/mm²

Puncture resistance : Min 300N

(ASTM E154:1993)

Water absorption @ 24hrs : <0.02%

(ASTM D570)

Water permeability

(DIN 1048:pt5:1991) : Nil

Tape Strength : Long 4.3 N/mm²

(ASTM D638:1991) Trans 5.8 N/mm²

Crack bridging

(ASTM C836:1995) : 1.5mm

Environmental Resistance: Conforms

(ASTM D543)

Resistance to Hydrostatic : 60m of water - ASTM D 5385

Head in Meters

Lap Adhesion Strength : 2200 N/m (2.2N/mm)

ASTM D 1000

Instructions for use

Surface preparation

Concrete surfaces should be float finished and free from cavities and projecting nibs. All surfaces shall be dry and free from frost, surface laitence and contamination.

Priming

Proofex Tack Coat must be applied to the substrate and allowed to dry until it is tack free, prior to the application of the membrane. All surfaces must be re-primed if left for more than 24 hours prior to the application of Proofex GP.

Application

Smooth transition should be made at wall/floor slab junctions using a sand/cement mortar and internal and external corners at walls and upstands pre-protected with Proofex Corner Pieces prior to the application of the membrane.

The membrane should be applied to the substrat having first removed the siliconised release paper, pressing the polyethylene film firmly ensuring that the adhesive bitumen compound bonds continuously to the substrate with no air pockets.

Allow at least a 75mm edge and a 150mm end lap. All laps should be rolled firmCICCCy to achieve a good seal. End laps should be staggered.

Proofex GP

(Formerly Proofex GPX)

On vertical or inclined surfaces, the membrane shall be laid from the lowest level upwards.

The membrane should be protected immediately after application in accordance with BS 8102 : 1990 by using Protection Board or as appropriate with a sand/cement screed.

Limitations

Application temperature range : 5°C - 50°C.

For application below 15°C it may be necessary to slightly warm the back of the membrane should be stored at temperatures above 20°C prior to application to facilitate ease of application and immediate bond to the substrate.

Estimating

Supply

Proofex GP : 10 m long x 1m wide roll

Proofex Tack Coat : 20 and 200 litre drums

Coverage

Proofex Tack Coat : 3-6m² per litre

Storage

All product have a shelf life of 12 months if stored in a cool, dry store, away from sources of heat, in the original unopened packing. It should be stored horizontally, not more than one pallet high.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

"Sapthagiri Palace", No.38,
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

++91 80-23551500

fax

++91 80-23551510

e-mail

enquiryindia@fosroc.com

Regional Offices

Bangalore

"Sapthagiri Palace", No. 38
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032.
Ph:080-23551500
Fax : 080-23551510

Mumbai

1401/1402, 14floor,
A-Wing 'The Great Eastern Summit'
Sector-15, CBD, Belapur
Navi Mumbai 400 614
Ph: 022 -43406800-04

Delhi

D-166 Sector 10
Noida,
UP 201 301
Ph:0120-4270620
Fax: 033-2499-0280

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph:033-65343188

www.fosroc.com

Precautions

Health and safety

There are no health hazards associated with the use of Proofex GP and Protection Board.

If proofex Tack Coat is swallowed, do not induce vomiting - drink a glass of water. If contact with eyes occurs, flood with copious amounts of clean water for at least 15 minutes and seek medical advice. If on the skin, remove any contaminated clothing and wash skin thoroughly.

For further information, please consult Material Safety Data Sheets for the above products.

Fire

Proofex GP and Protection Board are flammable. Keep away from sources of ignition. Do not smoke in the presence of these products. Proofex Tack Coat contains volatile flammable solvents. Use only in ventilated areas, well away from any ignition source.

Flash points

Proofex GP : > 65°C

Proofex Tack Coat : > 38°C

